# Surface modification of Co-doped ZnO nanocrystals and its effects on the magnetic properties

A. S. Pereira

Departamento de Química and CICECO, Universidade de Aveiro, P-3810-193 Aveiro, Portugal

### A. O. Ankiewicz<sup>a)</sup>

13 N-Institute for Nanostructures, Nanomodelling and Nanomanufacturing and Departamento de Física, Universidade de Aveiro, P-3810-193 Aveiro, Portugal and Institut für Experimentelle Physik II, Universität Leipzig, D-04103 Leipzig, Germany

### W. Gehlhoff and A. Hoffmann

Institut für Festkörperphysik, Technische Universität Berlin, D-10623 Berlin, Germany

#### S. Pereira and T. Trindade

CICECO, Universidade de Aveiro, P-3810-193 Aveiro, Portugal

#### M. Grundmann

Institut für Experimentelle Physik II, Universität Leipzig, D-04103 Leipzig, Germany

#### M. C. Carmo and N. A. Sobolev

13 N-Institute for Nanostructures, Nanomodelling and Nanomanufacturing and Departamento de Física, Universidade de Aveiro, P-3810-193 Aveiro, Portugal

(Presented on 6 November 2007; received 11 September 2007; accepted 25 October 2007; published online 18 March 2008)

A series of chemically prepared  $Co^{2+}$ -doped ZnO colloids has been surface modified either by growing shells of ZnSe or by the *in situ* encapsulation in poly(styrene). The surface modification effects using these two distinct chemical strategies on the magnetic properties of the nanocrystals were probed by electron paramagnetic resonance (EPR). Structural characterization by means of x-ray diffraction and transmission electron microscopy gave no evidence of second phase formation within the detection limits of the used equipment. The EPR analysis was carried out by simulations of the powderlike EPR spectra. The results confirm that in the core of these nanocrystals Co was incorporated as  $Co^{2+}$ , occupying the Zn<sup>2+</sup> sites in the wurtzite structure of ZnO. Additionally we identify two Co signals stemming from the nanocrystals' shell. The performed surface modifications clearly change the relative intensity of the EPR spectrum components, revealing the core and shell signals. © 2008 American Institute of Physics. [DOI: 10.1063/1.2833300]

# INTRODUCTION

Magnetic semiconductors combining properties and functionalities of both semiconductors and ferromagnets are driving an enormous scientific activity due to their potential applications in spintronics.<sup>1,2</sup> ZnO based diluted magnetic semiconductors are particularly promising due to their large band gap and to the possibility of achieving room temperature charge mediated ferromagnetism. Some groups have reported ferromagnetism in transition metal doped ZnO systems with Curie temperatures  $T_C$  ranging from 30 to 550 K,  $^{3-13}$  while others have found antiferromagnetic, spin glass, or paramagnetic behavior.<sup>14–19</sup> Thus, the topic is still controversial and further investigations are needed to clarify these materials' magnetic properties that are very sensitive to the preparation method. Simultaneously, there have been great efforts toward achieving high quality ZnO nanocrystals (NCs),<sup>6,7</sup> where surface related effects are especially relevant due to the high surface-to-volume ratio. In particular, for metal doped NCs, little is known about the effects of chemical surface modification strategies on doping. We

present a detailed investigation of the influence of the surface modification, namely, polymer encapsulation and inorganic capping, on the magnetic properties of Co-doped ZnO colloidal NCs. The magnetic and structural properties were probed by electron paramagnetic resonance (EPR), x-ray diffraction (XRD), and transmission electron microscopy (TEM).

# SAMPLE PREPARATION

All chemicals were supplied by Aldrich, except ethyl acetate (Lab-Scan). All the chemicals were used as received, except the organic solvents which were dried over molecular sieves. The doped ZnO colloids were synthesized by the dropwise addition of 33.3 cm<sup>3</sup> of absolute ethanol containing tetramethylammonium hydroxide  $(N(CH_3)_4OH \cdot 5H_2O:$ 0.552 mol dm<sup>-3</sup>) to  $Zn^{2+}$ : Co<sup>2+</sup> dimethylsulfoxide (DMSO) solutions.<sup>7</sup> These solutions were prepared by adding  $100 \text{ cm}^{3}$  $Co(CH_3COO)_2 \cdot 6H_2O$ to of a DMSO 0.101 mol dm<sup>-3</sup> solution in  $Zn(CH_3COO)_2 \cdot 2H_2O$  to achieve a 5% nominal mole doping. To extract the Co-doped ZnO NCs as powders (sample A), ethyl acetate was added to the colloid; the formed precipitate was centrifuged and washed

0021-8979/2008/103(7)/07D140/3/\$23.00

103, 07D140-1

<sup>&</sup>lt;sup>a)</sup>Electronic mail: amelia@ua.pt.



FIG. 1. TEM images of (a) ZnO:Co NCs (sample A), (b) polystyrene/ ZnO:Co nanocomposites (sample B), and (c) ZnO:Co NCs capped with ZnSe (sample C). The inferior part of the figure shows the XRD results for all three samples. The peak identification given for sample C is the same as for samples A and B.

with ethyl acetate and methanol. Trioctylphosphine oxide (TOPO) capped Co-doped ZnO NCs, obtained after thermal treatment of part of sample A at 150 °C for 4 h under a nitrogen stream, were thoroughly washed with methanol and subjected to chemical surface modification by two distinct routes.

- (1) A miniemulsion polymerization technique was employed to prepare poly(styrene) (PS) nanocomposites containing  $Co^{2+}$ -doped ZnO NCs. The miniemulsion was prepared by mixing a solution containing H<sub>2</sub>O (17.7399 g), NaHCO<sub>3</sub> (11.9 mg), and SDS (57.5 mg), with another solution containing ZnO:Co (6 mg), styrene (4 ml), hexadecane (82.1 mg), and AIBN (11.5 mg). These two solutions were mixed and stirred for 30 min and sonicated for 5 min. The reacting mixture was held 2 h at 70 °C after being purged with N<sub>2</sub> for 20 min. The final nanocomposite (sample B) was retrieved through centrifugation and washed with water to remove excess of PS.
- (2) In another strategy, the surface modification of the NCs was achieved by dispersing them in 2 cm<sup>3</sup> of TOP and heating the mixture up to 280 °C under a N<sub>2</sub> stream. An excess of TOPSe (2 mol dm<sup>-3</sup>) was then injected into the hot mixture and the reaction was kept at this temperature for 4 h, under N<sub>2</sub>. During this process, the formation of ZnSe at the ZnO surfaces was monitored by UV/visible spectroscopy. The extraction and washing of the NCs (sample C) were performed with a mixture (1:3) of methanol and isopropanol.

# STRUCTURAL CHARACTERIZATION

In Fig. 1 we show the TEM images together with the XRD measurements for all three samples. XRD evidenced the formation of ZnO NCs with a hexagonal wurtzite crystal structure for all samples. No Co clusters or Co-related complexes were detected, at least within the sensitivity of the apparatus. Excluding instrument broadening effects [using a certified standard NIST SRM660a (LaB<sub>6</sub> powder)] and ap-



FIG. 2. Experimental EPR spectrum taken at 10 K of ZnO:Co (nominal Co content of 5%) nanocrystals along with the respective simulation carried out by adding the EPR signals  $S_{\rm I}$ ,  $S_{\rm II}$ , and  $S_{\rm III}$ .

plying the Scherrer equation, we estimate the crystallite size as a function of the peak width, yielding average diameters of  $6 \pm 2$ ,  $6 \pm 2$ , and  $12 \pm 3$  nm for the NCs in samples A, B, and C, respectively. UV/visible absorption of the 5% Codoped ZnO NCs dispersed in dimethylsulfoxide exhibits the characteristic optical spectrum of a colloid containing ZnO NCs, revealing the well known absorption spectrum of Co<sup>2+</sup> ions in tetrahedral coordination geometry.<sup>19</sup> The TEM image shown in Fig. 1(b) exhibits that each nanocomposite particle of sample B results from the PS encapsulation of a group of ZnO:Co NCs forming morphologically well-defined particles with a ZnO phase (dark spots) dispersed in round shaped PS beads, in agreement with our previous findings for other systems.<sup>20,21</sup> The absorbance spectrum of sample C exhibits the development of an optical feature in the visible region of the spectrum (430–450 nm), which is ascribed to the formation of ZnSe. Figure 1(c) shows a TEM image obtained after 20 min reaction, evidencing fairly morphologically homogenous nanoparticles.

#### **EPR ANALYSIS**

EPR measurements were performed in the X(~9.5 GHz) and Q (and ~34 GHz) bands for all ZnO NC samples, at temperatures between 4 and 300 K, using a Bruker ESP 300E spectrometer equipped with Oxford Instruments continuous flow helium cryostats. In the case of substitutional  $Co^{2+}$  (3 $d^7$ ) on the Zn sites the ground state is the orbital singlet  ${}^{4}A_{2}$  and, due to the strong hexagonal crystal field, the zero-field splitting is much larger than the Zeeman energy; consequently only the electron spin transitions within the  $|\pm\frac{1}{2}\rangle$  doublet can be observed in the available magnetic field range. Thus, we can describe the spectra within a good approach by the formalism presented in Ref. 16 considering an effective electronic spin of S' = 1/2 and a nuclear spin of I=7/2. We simulate the EPR powder spectra by diagonalization of the spin Hamiltonian (SH) and fully integrating over the space angles using the EASYSPIN software package.<sup>22</sup> Illustratively, the simulations of the three EPR signals for sample A are shown in Fig. 2. Figure 3 presents the final result of the simulations of the EPR spectra for all samples with the respective experimental traces. The analysis proves that part of the spectra  $(S_I)$  is due to substitutional Co<sup>2+</sup> with effective SH parameters  $g'_{\parallel} = 2.2$ ,  $g'_{\perp} = 4.6$ ,  $A'_{\parallel} = 16.0 \times 10^{-4} \text{ cm}^{-1}$ , and  $A'_{\perp} = 3.0 \times 10^{-4} \text{ cm}^{-1}$ , in agree-



FIG. 3. Experimental EPR spectra taken at 10 K of ZnO:Co (nominal Co content of 5%) raw nanocrystals (sample A), of that after polymer encapsulation (sample B), or after reaction with TOPSe (sample C). In light gray are plotted the respective simulations carried out by adding the EPR signals  $S_{II}$ ,  $S_{III}$ , and  $S_{III}$ .

ment with the bulk values,<sup>23</sup> where g' is the effective g value, A' is the effective hyperfine constant, and the symbols  $\parallel$  and  $\perp$  designate the applied magnetic field parallel and perpendicular to the c axis, respectively. Additionally, there are two other Co lines,  $S_{\text{II}}$  and  $S_{\text{III}}$ , which are caused by a locally distorted environment and can be described by  $g'_{\parallel} = 2.2$  and  $g'_{\perp} = 5.3$ , and  $g'_{\parallel} = 2.2$  as well as  $g'_{\perp} = 3.9$  for  $S_{\text{II}}$  and  $S_{\text{III}}$ , respectively, as confirmed by Q-band measurements (not shown here), which have a higher spectral resolution. The surface exchange reaction with TOPSe occurring during the preparation of sample C, in which ZnSe is formed at the expense of Zn on the shell of the NCs, partially removes the  $S_{\text{II}}$  and  $S_{\text{III}}$  signals, revealing a core-shell structure. As expected, this effect is not so pronounced for sample B, as the surface is not removed by the PS encapsulation.

## **CONCLUDING REMARKS**

We have incorporated Co ions in ZnO colloidal NCs and subsequently modified their surfaces by PS encapsulation or by forming a ZnSe shell on their surface. By EPR spectroscopy we are able to distinguish three different signals: one coming from substitutional  $Co^{2+}$  in the NC core with SH parameters similar to the bulk ones and two other Co lines caused by locally distorted environment in the shell. No evidence of ferromagnetism was found in this series of samples. The core-shell structure is also proved by partially removing the shell signal when ZnSe is formed at the expense of Zn on the shell of the NCs, i.e., "etching" the shell. As the surface shell is not removed by the PS encapsulation, this effect is not so pronounced for this surface modification procedure.

## ACKNOWLEDGMENTS

This work has been supported by the SANDiE Network of Excellence of the EU, by the Fundação para a Ciência e a Tecnologia of Portugal, and FEDER for funding (Project Nos. PTDC/FIS/72843/2006 and PTDC/QUI/67712/2006; and Grant Nos. SFRH/BD/16985/2004 and SFRH/BD/ 21659/2005).

- <sup>1</sup>C. Liu, F. Yun, and H. Morkoç, J. Mater. Sci.: Mater. Electron. **16**, 555 (2005).
- <sup>2</sup>T. Dietl, J. Phys.: Condens. Matter 19, 165204 (2007).
- <sup>3</sup>S. W. Jung, S.-J. An, G.-C. Yi, C. U. Jung, S.-I. Lee, and S. Cho, Appl. Phys. Lett. **80**, 4561 (2002).
- <sup>4</sup>Y. W. Heo, M. P. Ivill, K. Ip, D. P. Norton, and S. J. Pearton, Appl. Phys. Lett. **84**, 2292 (2004).
- <sup>5</sup>D. P. Norton, S. J. Pearton, A. F. Herbard, N. Theodoropoulou, L. A. Boatner, and R. G. Wilson, Appl. Phys. Lett. **82**, 239 (2003).
- <sup>6</sup>N. S. Norberg, K. R. Kittilstved, J. E. Amonette, R. K. Kukkadapu, D. A. Schwartz, and D. R. Gamelin, J. Am. Chem. Soc. **126**, 9387 (2004).
- <sup>7</sup>D. A. Schwartz, N. S. Norberg, Q. P. Nguyen, J. M. Parker, and D. R. Gamelin, J. Am. Chem. Soc. **125**, 13205 (2003).
- <sup>8</sup>H.-J. Lee, S.-Y. Jeong, C. R. Cho, and C. H. Park, Appl. Phys. Lett. **81**, 4020 (2002).
- <sup>9</sup>Y. M. Cho, W. K. Choo, H. Kim, D. Kim, and Y. E. Ihm, Appl. Phys. Lett. **80**, 3358 (2002).
- <sup>10</sup>P. Sharma, A. Gupta, K. V. Rao, F. J. Owens, R. Sharma, R. Ahuja, J. M. Osorio Guillen, B. Johansson, and G. A. Gehring, Nat. Mater. 2, 673 (2003).
- <sup>11</sup>K. Ueda, H. Tabat, and T. Kawai, Appl. Phys. Lett. **79**, 988 (2001).
- <sup>12</sup>T. Wakano, N. Fujimura, Y. Morinaga, N. Abe, A. Ashida, and T. Ito, Physica E (Amsterdam) **10**, 260 (2001).
- <sup>13</sup>H. Saeki, H. Tabata, and T. Kawai, Solid State Commun. **120**, 439 (2001).
- <sup>14</sup>J. H. Kim, H. Kim, Y. E. Ihm, and W. K. Choo, J. Appl. Phys. **92**, 6066 (2002).
- <sup>15</sup>T. Fukumura, Z. Jin, M. Kawasaki, T. Shono, T. Hasegawa, S. Koshihara, and H. Koinuma, Appl. Phys. Lett. **78**, 958 (2001).
- <sup>16</sup>A. O. Ankiewicz, W. Gehlhoff, E. M. Kaidashev, A. Rahm, M. Lorenz, M. Grundmann, M. C. Carmo, and N. A. Sobolev, J. Appl. Phys. **101**, 024324 (2007).
- <sup>17</sup>M. H. Kane, K. Shalini, C. J. Summers, R. Varatharajan, J. Nause, C. R. Vestal, Z. J. Zhang, and I. T. Ferguson, J. Appl. Phys. 97, 023906 (2005).
- <sup>18</sup>M. Diaconu, H. Schmidt, A. Pöppl, R. Böttcher, J. Hoentsch, A. Rahm, H. Hochmuth, M. Lorenz, and M. Grundmann, Superlattices Microstruct. 38, 413 (2005).
- <sup>19</sup>N. Volbers, H. Zhou, C. Knies, D. Pfisterer, J. Sann, D. M. Hofmann, and B. K. Meyer, Appl. Phys. A: Mater. Sci. Process. 88, 153 (2007).
- <sup>20</sup>A. C. C. Esteves, A. Barros-Timmons, T. Monteiro, and T. Trindade, J. Nanosci. Nanotechnol. 5, 766 (2005).
- <sup>21</sup>M. A. Martins, M. C. Neves, A. C. C. Esteves, P. I. Girginova, A. J. Guiomar, V. S. Amaral, and T. Trindade, Nanotechnology **18**, 215609 (2007).
- <sup>22</sup>S. Stoll and A. Schweiger, J. Magn. Reson. **178**, 42 (2006).
- <sup>23</sup>T. L. Estle and M. De Witt, Bull. Am. Phys. Soc. 6(5), 445 (1961).